

## RUTEC® Projectionpaper 250g/m<sup>2</sup> (1480)

### TECHNICAL SPECIFICATIONS

Grammage (ISO 536)	250 g/m <sup>2</sup> (± 5 %)
Grammage PE liner (ISO 536)	25 g/m <sup>2</sup> ± 10 %
Tensile strength along (ISO 1924-2) MD	26 kN/m
Tensile strength transverse (ISO 1924-2) CD	15 kN/m
Tensile strength longitudinal (ISO 1974) MD	4,0 N
Tear resistance transverse (ISO 1974) CD	4,5 N
Whiteness (DIN 5033)	79 - 81 %
Bursting pressure (ISO 2758)	1.500 kPa

(Stand: 12/2013)

### STANDARD-AUSFÜHRUNGEN

Roll width	2.640 mm - 4.180 mm
Roll length	60 lfm
Housing diameter	95 mm
2 Notches	15 mm breit, 40 mm tief

Information given here represents our experience. There are no specifications. Before using our products, please check whether they are suitable for the purpose intended by you individually.

Download the Datasheet as PDF

